

Product Description

Somos® WaterClear Ultra 10122 is an optically clear stereolithography material that is easy to use and fast to build. This material produces colorless, functional and accurate parts that simulate an acrylic appearance. Parts produced with Somos® WaterClear Ultra 10122 exhibit excellent temperature resistance.

Somos® WaterClear Ultra 10122 is ideal for applications such as master patterns, concept and functional models. This material also provides refractive values similar to engineered plastics for functional testing in optical light transmission work.

Key Benefits

- Extraordinary optical clarity
- Superior moisture resistance
- Easy to use and finish

Ideal Applications

- Automotive lenses
- Bottles
- Lenses
- Light pipes



Somos® WaterClear Ultra 10122 Technical Data

Liquid Properties		Optical Properties			
Appearance	Optically clear, colorless	E _c	10.0 mJ/cm ²	[critical exposure]	
Viscosity	~165 cps @ 30°C	D _P	6.5 mils	[slope of cure-depth vs. In (E) curve]	
Density	~1.13 g/cm³ @ 25°C	E ₁₀	47 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]	
		D542	1.52	Index of Refraction (cured)	

Mechanical Properties		UV Postcure		
ASTM Method	Property Description	Metric	Imperial	
D638M	Tensile Strength at Break	56 MPa	8.1 ksi	
D638M	Tensile Modulus	2,880 MPa	418 ksi	
D638M	Elongation at Break	7.5%		
D638M	Elongation at Yield	4%		
D638M	Poisson's Ratio	0.41		
D790M	Flexural Strength	84 MPa	12.2 ksi	
D2240	Flexural Modulus	2,490 MPa	361 ksi	
D256A	Izod Impact (Notched)	25 J/m	0.47 ft-lb/in	
D2240	Hardness (Shore D)	87		
D570-98	Water Absorption	1.1%		
Thermal/Electrical Properties		UV Postcure		
ASTM Method	Property Description	Metric	Imperial	
E831-05	C.T.E40 - 0°C (-40 - 32°F)	65 µm/m°C	36 μin/in°F	
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	90 μm/m°C	50 μin/in°F	
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	168 μm/m°C	93 μin/in°F	
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	159 μm/m°C	88 μin/in°F	
D150-98	Dielectric Constant 60 Hz	3.1		
D150-98	Dielectric Constant 1 KHz	3.5		
D150-98	Dielectric Constant 1 MHz	3.1		
D149-97a	Dielectric Strength	15.0 kV/mm	381 V/mil	
E1545-00	Tg	44°C	111°F	
D648	HDT @ 0.46 MPa (66 psi)	47°C	117°F	
D648	HDT @ 1.81 MPa (264 psi)	43°C	109°F	
D648	Thermal Postcure: HDT @ 0.46 MPa (66 psi)	60°C	140°F	
D648	Thermal Postcure: HDT @ 1.81 MPa (264 psi)	50°C	122°F	

These values may vary and depend on individual machine processing and post-curing practices.

DSM Functional Materials Somos® Material Group

North America

USA

1122 St. Charles Street Elgin, Illinois 60120

Phone: +1.847.697.0400

Europe

Slachthuisweg 30 3151 XN Hoek van Holland The Netherlands Phone: +31.174.315.391

China

476 Li Bing Road Zhangjiang Hi-Tech Park Pudong New Area Shanghai 201203, China Phone: +86.21.6141.8064 NOTICE: Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties are provided by the product of the product on processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2015 DSM IP ASSESTS B.V. All rights reserved.